

CT 48



Silicone paint

Hydrophobic, vapour permeable paint for buildings' façades and interiors

CHARACTERISTICS

- ▶ low absorbability
- ▶ vapour permeable (breathable)
- ▶ resistant to dirt
- ▶ durable
- ▶ highly resistant to weather conditions and UV resistant
- ▶ BioProtect formula – resistant to the development of fungi, algae and mould
- ▶ available in full palette of Ceresit Colours of Nature®

Colour System



SCOPE OF USE

Ceresit CT 48 is used for protecting façades, concrete constructions, interiors. It can be applied on the mineral substrates (concrete, cement plasters, lime-cement plasters and lime plasters). CT 48 can be used for painting Ceresit CT 34, CT 35 and CT 137 mineral plasters, Ceresit CT 60, CT 63, CT 64 acrylic plasters, Ceresit CT 72, CT 73 silicate plasters, Ceresit CT 174, CT 175 silicate-silicone plasters as well as silicone plasters Ceresit CT 74, CT 75 and elastomeric plaster Ceresit CT 79 applied on traditional substrates and within Ceresit ETICS (External Thermal Insulation Composite Systems) with the application of EPS-boards (Expanded Polystyrene boards). The structure of the coating ensures fast moisture evaporation from the substrate and at the same time creates efficient protection against the substrate moisture and humidity. The binder used in the paint CT 48 causes pearl like effect of water after wetting the coat. It is highly recommended to use CT 48 in historical objects, on the renovation and aerated plasters as well as on all the surfaces where aesthetic qualities and duration of the coating is required. The façades covered with the paint CT 48 can be washed with washing devices operating under low pressure. The exposure of the façade to the sun causes dangerous tensions, therefore dark colours should be used only on small areas, e.g. architectural details. The paint has protection from biological contamination, such as fungi, mould or algae, increasing its resistance to their effects.



CERESIT_C_CT48_TDS_1_0116

SUBSTRATE PREPARATION

The paint CT 48 may be applied on carrying, smooth, dry and clean substrates (free from any substances that decrease adhesion such as grease, bitumen, dust):

- concrete (age over 28 days)
 - traditional cement plasters, lime-cement plasters and lime plasters (age over 14 days),
 - thin-layer mineral and mineral-polymer plasters (age over 7 days),
 - thin-layer acrylic and silicone plasters (age over 3 days),
 - thin-layer silicate plasters (age over 5 days),
 - gypsum substrates (only inside the buildings) with the humidity below 1%, firstly primed with Ceresit CT 17,
 - gypsum cardboards, gypsum-fibre boards (only inside the buildings), fixed according to the recommendations of the board manufactures, firstly primed with CT 17,
 - strong paint coats with good adhesion to the substrate.
- Firstly, uneven and damaged substrates should be repaired. Plaster filler Ceresit CT 29 can be used for repairs. It is recommended to check the strength of the existing mineral layers. The existing dirt, layers of low strength, lime and adhesive paint coatings, as well as the remainders of wall paper or glues should be completely removed. It is recommended to use wa-

shing devices with the use of an agent for removing impurities. After being washed with water, the substrate should dry.

APPLICATION

Before the paint application, the content of the container should be carefully stirred by means of a drill with a mixer for about 2 minutes. Usually it is sufficient to paint twice. Between the application of the subsequent layers at least 12- to 24-hour technological breaks should be maintained. CT 48 should be applied by means of a brush, roller or a sprinkling device. It is important to apply the paint evenly. If there is such a need, it is possible to add not more than 5 % of water and stir carefully. Neither rusty containers nor tools should be used. Work on one surface should be carried on without any breaks using the paint of the same badge number printed on each packaging or the content of containers with different badge numbers should be mixed together. Application with spray machine using pressure machines e.g. Wagner PS 22 or PS 30, nozzle 517, pressure 160-200 bar, performance of machine 12 l/min. The area not to be painted, e.g. windows, doors should be protected (e.g. with foil). Bushes, other plants, etc. should be protected as well. Any stains should be immediately rinsed with water. Tools should be washed carefully with water directly after being used.

PLEASE NOTE

Application should be performed in dry conditions with the ambient and substrate temperature ranging from +5 °C to +25 °C and the humidity below 80 %. The paint may cause decolouration impossible to be removed on glass, ceramic, wooden, metal and stone surfaces, therefore all the elements in contact with CT 48 should be protected. Skin and eyes should be protected. Protective gloves and glasses should be worn while applying the paint. Stains should be carefully rinsed with water. In case of contact with eyes, they should be rinsed with water and the general

Apart from the information given here it is also important to observe the relevant guidelines and regulations of various organisations and trade associations as well as the respective standards of the German Standards Institute (DIN). The aforementioned characteristics are based on practical experience and applied testing. Warranted properties and possible uses which go beyond those warranted in this information sheet require our written confirmation. All data given was obtained at an ambient and material temperature of +23 °C and 50 % relative air humidity unless specified otherwise. Please note that under other climatic conditions hardening can be accelerated or delayed.

The information contained herein, particularly recommendations for the handling and use of our products, is based on our professional experience. As materials and conditions may vary with each intended application, and thus are beyond our sphere of influence, we strongly recommend that in each case sufficient tests are conducted to check the suitability of our products for their intended use. Legal liability cannot be accepted on the basis of the contents of this data sheet or any verbal advice given, unless there is a case of wilful misconduct or gross negligence on our part. This technical data sheet supersedes all previous editions relevant to this product.



Henkel CEE
Erdbergstrasse 29
1030 Vienna
www.ceresit.com

practitioner should be consulted. This product should be stored out of reach of children.

OTHER INFORMATION

This paint should not be applied on strongly sunny surfaces. The façade should be protected against rain until the paint dries completely. It is recommended to use scaffolding protection. The opened container should be carefully closed and its content should be used as soon as possible. Do not apply paint to the substrate with increased alkalinity (eg. fresh mineral plaster, mineral substrates), it may cause adverse alkaline effects on the paint coat and pigments.

PACKAGING

Plastic containers of 3,5 and 15 l.

TECHNICAL DATA

Base:	modified silicone and acrylic resins with fillers and pigments
Density:	approx. 1.45 kg/dm ³
Temperature of application:	from +5 °C to +25 °C
Resistance to rain:	after approx. 3 h
Assumed consumption:	depending on the smoothness and absorption of the substrate, on average approx. 0.3 l/m ² with two coatings
Vapour permeability acc. EN 1062:	$S_d \leq 0,08$ m
Water permeability acc. EN 1062:	W3
Water vapour penetration acc. to EN 1062:	V1
Shine acc. EN 1062:	G3
Grain size acc. EN 1062:	S1
Assess the degree of blistering acc. EN 1062:	lack
Evaluation of the cracks acc. EN 1062:	cat. 0, lack
Assessment of the degree of exfoliation acc. EN 1062:	cat. 0, lack

Fire classification: acc. EN 13501-1:

A2-s1, d0 in:

Ceresit Ceretherm Wool Classic, Ceresit Ceretherm Wool Premium

B – s1, d0 in:

Ceresit Ceretherm Popular, Ceresit Ceretherm Classic,

Ceresit Ceretherm Premium, Ceresit Ceretherm Express

pH: approx. 8,5

Shelf life/ Storage: up to 12 months since the production date when stored in cool conditions and in original undamaged packages.

Protect against frost! Protect against direct sunlight!

This product possesses documents of reference:

- Permission of the Minister of Health for the trading in the biocide product NO. 3353/07;
- BBA Certificate No. 14/5142
- Irish Agreement Board Certificate No. 09/0340
- European Technical Approval (ETA) in systems:

Ceresit Ceretherm System	Popular	Classic	Premium	Universal EPS	Universal XPS	Universal MW	Wool Classic	Wool Premium
ETA	08/0309	09/0014	08/0308	13/0535	13/0807	14/0127	09/0026	09/0037
Certificate	1488-CPR-0382/Z	1488-CPD-0104/W	1488-CPR-0363/Z	1488-CPD-0418/W	1488-CPD-0419/W	1488-CPR-0362/Z	1488-CPD-0127/W	1488-CPR-0375/Z
DoP	00426/28-01-2015	00420/01-07-2013	00428/06-08-2014	00433/01-07-2013	00434/01-07-2013	00435/06-08-2014	00424/01-07-2013	00430/17-11-2014

- Technical Approvals in Systems:

Ceresit Ceretherm System	Popular	Classic	Express	Reno
TA	15-6894/2013+ Annexes	15-4397/2013	15-7152/2010+ Annexes	15-8077/2009+ Annexes
Certificate	ITB-0068/Z	ITB-0109/Z	ITB-0173/Z	ITB-0355/Z
DoC	00442/15-04-2013	00440/01-07-2013	00441/27-03-2015	00444/12-08-2015

Quality for Professionals