

Data sheet: SkamolEnclosure Board

Grade	Value	Unit
Maximum service temperature	1,000	°C
	1,832	°F
Bulk density, dry	225	kg/m ³
	14	lbs/ft ³
Cold crushing strength (DS/EN ISO 8895_2006)	2.8	MPa
	406	lbs/in ²
Modulus of rupture (EN 993-6:1995)	1.4	MPa
	203	lbs/in ²
Total porosity (EN 1094-4:1995)	91	%
Permeability to gases (EN 993-4:1995)	0.7	nPm
Specific heat	0.84	kJ/(kg×K)
	0.20	BTU/(lb×°F)
Coefficient of reversible thermal expansion @ 20 - 750°C (68 - 1,382°F)	5.5	×10 ⁻⁶ K ⁻¹
	3.1	×10 ⁻⁶ °F ⁻¹
Tensile strength (EN 1607)	610	kPa
	88.47	lbs/in ²
Dimension stability under specified temperature and humidity conditions (EN 1604) @ 23°C - 90%RH - 48 h	0.0	%

Chemical analysis, typical		
Silica	SiO ₂	47 %
Ferric oxide	Fe ₂ O ₃	0.1 %
Alumina	Al ₂ O ₃	0.2 %
Magnesium oxide	MgO	0.4 %
Calcium oxide	CaO	42 %
Sodium oxide	Na ₂ O	0.1 %
Potassium oxide	K ₂ O	0.1 %
Loss on ignition @ 1,025°C (1,877°F)	LOI	9 %

Non-combustibility tests (EN 13501-1:2007 + A1:2009)	Class A1
HS Tariff number (Harmonized Commodity Description and Coding System)	6806.90.00
Colour	GREY

Data are average results of tests conducted under standard procedures and are subject to variation.

Data contained in this data sheet are supplied in good faith as a technical service and are subject to change without notice. Misprint and errors excepted.

Revision number: 07-02-2018

Skamol

Østergade 58-60, 7900 Nykøbing Mors, Denmark

Tel.: +45 97 72 15 33

www.skamol.com

