

STS Ltd 5 Hawthorn Park Seacroft LS14 1PQ T: +44 (0)113 202 2010 E: sales@sts-uk.com

Technical Data

XPS Insulation 10mm Insulation Board 1200x600mm

NoMorePly Insulation Backing Boards are made of high-performance waterproof extruded polystyrene, there is approx. 1mm of coating on either side comprising a glass fibre mesh embedded in a polymer-cement mortar.

Technical Data

Specification		
Board Weight	1.7kg	
Tolerance	+/- 2%	
Properties of the Foam Componant		
Density	235 kg/m3	
Thermal Conductivity	0.034 W/mK	
Compressive Strength	Minimum of 0.3N/mm2	
Flexural Strength	0.30 ± 0.02 MPa	
Water Absorption (2-day immersion)	0.2% by volume	
Water Absorption (Capillary)	Zero	
Coefficient of linear expansion	70 x 10-6 K-1	
Water Vapour Diffusion Resistivity (µ)	110 - 225 µ	
Water Vapour Permeability	0.028 ng/Pa.m.s	
EU controlled substances content	None	



STS Ltd 5 Hawthorn Park Seacroft LS14 1PQ T: +44 (0)113 202 2010 E: sales@sts-uk.com

Technical Data

XPS Insulation 10mm Insulation Board 1200x600mm

Technical Data Continued

Properties of the Cement Coating	
Thermal Conductivity	0.034 W/mK
Compressive Strength	Minimum of 0.3N/mm2
Bond Strength	0.3N/mm2
Maximum Tile Loading Weight	62kg/m2
Flexural Strength	0.30 ± 0.02 MPa
Water Vapour Permeability (Sd)	3.2m
Resistance to body impact	3 x 120N/m
Bending Stiffness, E(20mm)	601KNmm2
Coefficient of linear expansion	30 x 10-6 K-1
Flammability	Class E
Impact Sound Reduction	dLw = 21
Shear Bond Strength	3.32kg/cm2
EU Controlled Substances Content	None

Thermal Insulation Values	
R Value	0.30 W/mK
U Value	3.33 W/m² x K
λd Rated value	0.034